







FR-LSH MULTICORE FLEXIBLE CABLE

Minimum bending radius

Document ID: TE/QMS/F/02	DESIGN CODE: LDIS09CYUAYL003C035S
Particulars	3 Core X 35 Sq.mm
Name of Manufacturer	Polycab India Ltd
Type of cable	YY
Voltage Grade V	1100
No of cores X size in sq.mm.	3 Core X 35 Sq.mm.
Conductor	
a) Material	Plain annealed high conductivity flexible copper conductor as per Class 5 of IS 8130/2013, latest
b) Max. d.c. resistance of conductor at 20° C (ohm/km)	0.554
c) Shape of the conductor	Flexible Circular
Insulation	
a) Material	PVC TYPE D as per IS 5831/1984, Latest
b) Nominal thickness (mm)	1.2
c) Core identification	Red, Black and Green
Outer Sheath	
a) Material	Extruded FR-LSH PVC Type ST3 as per IS 5831/1984, Latest
b) Nominal thickness (mm)	1.6
c) Colour of outer sheath	Black
Approx. overall diameter of the cable in mm	24.8 +/-2
Maximum conductor temperature under normal operating condition	70°C
Maximum conductor temperature at the terminal of short circuit	160°C
Electrical Parameters	
a) Max. a.c. resistance of conductor at operating temperature (Ohm/km)	0.663
b) High voltage test (kV)	3
Continuous Current carrying capacities :-	
a) In Air at 40°C (A)	106
Applicable Standard	IS 8130/2013, IS 5831/1984, IS 694/2010, etc. with latest up to date updates

8 times Overall diameter



Printing

CABLES

FR-LSH Properties

a) Oxygen Index Min. 29% as per ASTM D-2863

b) Temperature Index Min. 250 Deg. C as per ASTM D-2863

c) Smoke density ratting Max. 60% as per ASTM D -2843

d) Acid gas generation Max. 20% as per IEC 60754-1

Standard packing length 100 meter coil, 300 meter coil, 500 meter, 1000 meter

(Higher quantity in wodden drum)

POLYCAB FR-LSH<SIZE SQ.MM> 1100V IS: 694 <ISI LOGO>

CM/L - 2832257, HALOL - <CE MARKING>

Rev. No.: 00 Issued Date : 10/06/2021